

Hymod™ Prima



Hymod™
is a trade mark of
IMERYS Minerals Ltd

ECC is a business name of
IMERYS Minerals Ltd

The data quoted are determined by the use of Imerys Standard Test Methods, copies of which will be supplied on request. Every precaution is taken in production to ensure the products conform to our published data. Since the products are based on naturally occurring materials, we reserve the right to change these data should it become necessary. Sales are in accordance with our "Conditions of Sale", copies of which will be supplied on request.



FM14752

BS EN ISO 9001:2000

PRODUCT SPECIFICATION

Chemical Composition (mass %):

	Value	Range	
		Min	Max
SiO ₂	54	52	56
Fe ₂ O ₃	1,4	1,1	1,6
TiO ₂	1,2	0,9	1,4
K ₂ O	3,1	2,8	3,4

Surface Area (BET):

Value	Range
Min	Max
41	36 - 46

TYPICAL DATA

The following data is provided for information only and is derived from quality control tests over a number of years. It does not constitute a specification.

Chemical Composition (mass %):

Al ₂ O ₃	30,0
CaO	0,3
MgO	0,4
Na ₂ O	0,5
L.O.I	8,8

Particle Size (mass %):	Value
+125 microns	0,1
+53 microns	0,3
-5 microns	96
-2 microns	88
-1 micron	79
-0.5 micron	67

Modulus of Rupture (MNm⁻²):

Dried at 110°C	8,0
----------------	-----

Fired Properties:

Water Absorption (mass %)	1120°C	4,0
	1180°C	2,5
	1240°C	1,5
Brightness (%)	1120°C	62
	1180°C	54
	1240°C	49
Contraction (%)	1120°C	11,5
	1180°C	12,5
	1240°C	13,0

Casting Data:

Casting concentration (mass % solids)	61,5	
Na ₂ CO ₃ + M75 sodium silicate (mass %)	7 poise	1,9
	5 poise	2,1

Carbon (wt %):	0,3
----------------	-----

W.S. salts (wt %):	0,1
--------------------	-----

C1/323/B

April 2000

Hymod Prima

© IMERYS

Fourth Edition

This supercedes the

document C163

dated July 1994

IMERYS Minerals Ltd

Par Moor Centre

Par Moor Road

Par, Cornwall

PL24 2SQ, UK

Tel: +44 (0) 1726 81 8000

Fax: +44 (0) 1726 81 1200

