

Kentucky-Tennessee Clay Company

Basic Properties - Ball Clays

Gleason, TN | Mayfield, KY | Crenshaw, MS
Other Products and Applications

Gleason, Tennessee Ball Clays - Basic Properties

	S.S.A. m ² /g	% < 5 mic.	% < 0.5 mic.	Al ₂ O ₃	LOI
Bell Dark	22.3	84	53	27.3	10.6
J-4	24	90	63	28.7	10.3
HTP	24.7	90	57	31.1	10.8
J-2	25.4	85	55	26.6	11.0
Jackson	23.5	85	56	28.4	11.4
KT #1-4	18.8	79	38	27.4	10.3
KTS-2	18.4	75	38	23.4	9.7
KTS Classic	18.4	74	35	23.2	9.5
L-1	16.2	68	30	20.6	9.2
Martin #5	14.4	72	28	23.6	8.3
Martin #5/L-1	15.5	70	28	22.6	8.5
TN #1 SGP	18.0	80	37	27.4	10.3
TN #5	19.9	80	42	28.2	11.1
TN #6 Bond	21.3	84	51	24.8	10.1
TN #10	18.8	92	52	33.2	11.3
RBS Slurry	21.2	82	48	26.6	10.1

[Return to top](#)

Mayfield, Kentucky Ball Clays - Basic Properties

	S.S.A. m ² /g	% < 5 mic.	% < 0.5 mic.	Al ₂ O ₃	LOI
HA-5	20.9	90	40	27.7	9.8
MB	21	87	52	29.8	10.3
OSML	19	81	41	24.9	10.4
KY #5 Bond	20.9	90	40	27.7	9.8
KY Stone	20.0	70	36	21.4	7.6
KT-556	20.8	90	44	28.1	10.0
Old Mine #4	22.8	86	43	26.6	11.1
Todd Light	26.0	89	46	27.0	10.7
SB Clay	17.5	68	29	20.1	7.6

[Return to top](#)

Crenshaw, Mississippi Ball Clays - Basic Properties

	S.S.A. m ² /g	% < 5 mic.	% < 0.5 mic.	Al ₂ O ₃	LOI
CTS	37.1	93	71	27.8	9.8
M&D	43.1	97	78	27.8	10.8
3380	30.9	91	66	27.1	9.3
JASS	39.1	87	58	21.7	8.9

[Return to top](#)

Other Products and Applications

K-T Products:

[Ceramic Grade Ball Clays](#)

Ceramics Applications:

[Select from list...](#)

Filler Applications:

[Select from list...](#)

[Contact Us](#) | [Samples, Comments and Other Requests](#)
[Home](#) | [Corporate Philosophy](#) | [Environmental](#)
[Plants and Locations](#) | [Products](#) | [Tech Talk](#)
[International](#) | [Customer Service](#) | [Credit Application](#)
[News & Views](#) | [Ceramic Materials Links](#) | [ESPAÑOL](#)