

Kentucky-Tennessee Clay Company

Basic Properties - Kaolins

Sandersville, GA | Langley, SC
Other Products and Applications

Sandersville, Georgia Kaolins - Basic Properties

	S.S.A. m ² /g	% < 5 mic.	% < 0.5 mic.	Al ₂ O ₃	LOI
Allen	13.5	81.5	28	38.1	13.5
Allen G	13.5	81.5	28	38.5	13.6
Diamond	18	83	38	37.9	13.5
Ewing	12.5	79	24.5	38.6	13.7
Kaolin Slurry	13	78	23	38.2	13.5
Kingsley	12.5	80	25	38.4	13.6
Kingsley-Rogers		80	34	38.1	13.6
KT-Cast	12	75	21	38.8	13.6
KT-Cast/Rogers	13.5	81	30	38.1	13.6
optiKasT	11	74	18	38.7	13.7
optiKasT Slurry	11	74	18	38.7	13.7
Rogers	24	94	65	37.5	13.2
Samson	18	86	44	38.1	13.4
Sapphire	22	91	48	38.2	13.4
Supreme Slurry	15	81.5	27	39.2	13.6
Wilson	15	81	34	38.1	13.5

[Return to top](#)

Langley, South Carolina Kaolins - Basic Properties

	S.S.A. m ² /g	% < 5 mic.	% < 0.5 mic.	Al ₂ O ₃	LOI
Kaolex SC					13.5
Kaolex BN	26	98	71.5	38.8	14
Kaolex FG		-	-	-	13.5

[Return to top](#)

Other Products and Applications

K-T Products:	Ceramic Grade Kaolins	<input type="checkbox"/>
Ceramics Applications:	Select from list...	<input type="checkbox"/>
Filler Applications:	Select from list...	<input type="checkbox"/>